

# NEW PRODUCT SERIES

Technical Information Spec-sheet



**International  
Wholesale  
Tile, LLC**

SERIES NAME

Delhi

## TECHNICAL CHARACTERISTICS

Available Formats:	12x24, 24x24		
Style Description:	Solid Color	Glaze Application Method:	H.D.I.T. Inkjet
Visual Characteristics:	Plain White	Number of Faces/Screens:	1
Thickness in mm:	9mm	Number of Punches/Molds:	
Modular Suitability:	Yes	Body Type:	Porcelain
Application:	Residential/Commercial	Color Body Unglazed:	
Recycled Content: Post or Pre Customer		Surface Type:	Glossy/Polished/Flat
Rectified:	Yes	Recommended Grout Joint:	Yes

## PRODUCT TESTING INFORMATION

*Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)*

Water Absorption:	≤ 0.5	Static COF:	
Shade Variation (1, 2, 3, 4)	V2	Dynamic COF:	Dry: 2.52- Wet: 0.42
Scratch Hardness (MOHS)	5	Breaking Strength:	2689 N APPROX
Frost Resistant:	Yes	Thermal Shock Resistance:	Resistant
PEI/Abrasion Resistance:	5	Deep Abrasion Test <175mm <sup>2</sup> :	Yes
Chemical Resistance:	GA		

### Note:

Manufacturer does not recommend installing large format rectangular tile using a 50% staggered brick/running bond grout joint pattern. Joint locations can be random and should be positioned to be no less than 30% the length of the adjacent tile. Alternating joints so they are <30%, a straight-lay or herring bone patterns are acceptable and with grout joint sizes of 1/4" to 3/16" but no less than 1/8".

# NEW PRODUCT SERIES

Technical Information Spec-sheet



**International  
Wholesale  
Tile, LLC**

SERIES NAME

Delhi

## TECHNICAL CHARACTERISTICS

Available Formats:	32x32		
Style Description:	Solid Color	Glaze Application Method:	H.D.I.T. Inkjet
Visual Characteristics:	Plain White	Number of Faces/Screens:	1
Thickness in mm:	9.5mm	Number of Punches/Molds:	1
Modular Suitability:	Yes	Body Type:	Porcelain
Application:	Residential/Commercial	Color Body Unglazed:	
Recycled Content: Post or Pre Customer		Surface Type:	Glossy/Polished/Flat
Rectified:	Yes	Recommended Grout Joint:	2 mm

## PRODUCT TESTING INFORMATION

*Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)*

Water Absorption:	≤ 0.5	Static COF:	
Shade Variation (1, 2, 3, 4)	V2	Dynamic COF:	<0.4
Scratch Hardness (MOHS)	Min. 5	Breaking Strength:	Min. 1800 N
Frost Resistant:	Yes	Thermal Shock Resistance:	No Damage
PEI/Abrasion Resistance:	4	Deep Abrasion Test <175mm <sup>2</sup> :	Yes
Chemical Resistance:	GA		

*ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.*

# NEW PRODUCT SERIES

Technical Information Spec-sheet



**International  
Wholesale  
Tile, LLC**

SERIES NAME

**DELHI 24x48**

## TECHNICAL CHARACTERISTICS

Available Formats:	24x48		
Style Description:	Precious Stone	Glaze Application Method:	H.D.I.T. Inkjet
Visual Characteristics:	Plain White	Number of Faces/Screens:	1
Thickness in mm:	10MM	Number of Punches/Molds:	
Modular Suitability:	Yes	Body Type:	Porcelain (<.5%)
Application:	Residential/Commercial	Color Body Unglazed:	
Recycled Content: Post or Pre Customer		Surface Type:	Glossy/Polished
Rectified:	Yes	Recommended Grout Joint:	

## PRODUCT TESTING INFORMATION

*Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)*

Water Absorption:	≤0.5%	Static COF:	
Shade Variation (1, 2, 3, 4)	2	Dynamic COF:	
Scratch Hardness (MOHS)	5	Breaking Strength:	1685
Frost Resistant:	Yes	Thermal Shock Resistance:	YES
PEI/Abrasion Resistance:	IV	Deep Abrasion Test <175mm <sup>2</sup> :	YES
Chemical Resistance:	ULA		

*ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.*