

NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

SERIES NAME

LARIX

TECHNICAL CHARACTERISTICS

| | | | |
|---|-------------------------------------|---------------------------|--------------------------------|
| Available Formats: | 10x60, 6x30 and 24x24 Baita Pattern | | |
| Style Description: | Modern Wood | Glaze Application Method: | HDIT Inkjet |
| Visual Characteristics: | Textured Wood | Number of Faces/Screens: | 60 |
| Thickness in mm: | 10 | Number of Punches/Molds: | N/A |
| Modular Suitability: | 10x60: 63%, 6x30: 37% | Body Type: | Porcelain (< .5%) |
| Application: | Residential/Commercial | Color Body Unglazed: | Yes |
| Recycled Content: Post or Pre Customer | N/A | Surface Type: | Matte/Textured |
| Rectified: | Yes | Recommended Grout Joint: | No less than 1/8 th |

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

| | | | |
|------------------------------|----------|--|------------------------|
| Water Absorption: | < .5% | Static COF: | Wet: 0.67 Dry: 0.88 |
| Shade Variation (1, 2, 3, 4) | V3 | Dynamic COF: | 0.56 |
| Scratch Hardness (MOHS) | NPD | Breaking Strength: | Conforming ISO 10545-4 |
| Frost Resistant: | Yes | Thermal Shock Resistance: | Resistant |
| PEI/Abrasion Resistance: | IV | Deep Abrasion Test <175mm ² : | Yes |
| Chemical Resistance: | Conforms | | |

PACKING INFORMATION - 6x30 *Please inquire with Customer Service for additional sizes*

| | | | |
|------------------------|--------|---------------------|----------|
| SqFt per Carton: | 8.48 | Pieces per Carton: | 7 |
| SqFt per Pallet: | 407.04 | Pounds per Carton: | 38.5 lbs |
| Boxes per Pallet: | 48 | SqFt per Container: | N/A |
| Pallets per Container: | N/A | | |

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.