NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

| SERIES NAME | ASIA |
|-------------|------|
|-------------|------|

| TECHNICAL CHARACTERISTICS | | | | |
|---------------------------|------------------------|---------------------------|-----------------|--|
| Available Formats: | 9x45 | | | |
| Style Description: | Wood | Glaze Application Method: | H.D.I.T. Inkjet | |
| Visual Characteristics: | | Number of Faces/Screens: | 15 | |
| Thickness in mm: | 9 mm | Number of Punches/Molds: | 1 | |
| Modular Suitability: | No | Body Type: | Porcelain | |
| Application: | Residential/Commercial | Color Body Unglazed: | Sand White | |
| Recycled Content: | 4% | Surface Type: | Matte/Flat | |
| Post or Pre Customer | | | | |
| Rectified: | Yes | Recommended Grout Joint: | 2 mm | |

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

| Water Absorption: | <.5% | Static COF: | |
|------------------------------|--------|---------------------------|----------------|
| Shade Variation (1, 2, 3, 4) | V2 | Dynamic COF: | <u>>0.4</u> |
| Scratch Hardness (MOHS) | 5 | Breaking Strength: | >1500N |
| Frost Resistant: | Yes | Thermal Shock Resistance: | Yes |
| PEI/Abrasion Resistance: | 4 | Deep Abrasion Test | No |
| | | <175mm ² : | |
| Chemical Resistance: | >1500N | | |

| PACKING INFORMATION - | Please inquire with Customer Service for additional sizes | | |
|------------------------------|-----------------------------------------------------------|---------------------|---|
| SqFt per Carton: | 19.59 | Pieces per Carton: | 9 |
| SqFt per Pallet: | 940.32 | Pounds per Carton: | |
| Boxes per Pallet: | 48 | SqFt per Container: | |
| Pallets per Container: | 16 | | |

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.