

# NEW PRODUCT SERIES

Technical Information Spec-sheet



# International Wholesale Tile, LLC

SERIES NAME

ORIGIN

## TECHNICAL CHARACTERISTICS

Available Formats:	24x24		
Style Description:	Marble	Glaze Application Method:	Inkjet
Visual Characteristics:	Polished Marble	Number of Faces/Screens:	10
Thickness in mm:	9.5 MM	Number of Punches/Molds:	
Modular Suitability:		Body Type:	Porcelain
Application:	Residential/Commercial	Color Body Unglazed:	Glazed
Recycled Content: Post or Pre Customer		Surface Type:	Glossy/Polished/Flat
Rectified or Pressed	Rectified	Recommended Grout Joint:	

## PRODUCT TESTING INFORMATION

*Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)*

Water Absorption:	<0.05-0.12%	Static COF:	
Shade Variation (1, 2, 3, 4)	V2	Dynamic COF:	.22 Polished
Scratch Hardness (MOHS)	4.5	Breaking Strength:	2,000-2,500 N
Frost Resistant:	Yes	Thermal Shock Resistance:	Pass after 10 cycles
PEI/Abrasion Resistance:	2	Deep Abrasion Test <175mm <sup>2</sup> :	No
Chemical Resistance:	GA/GLA/GHA		

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.

# NEW PRODUCT SERIES

Technical Information Spec-sheet



## International Wholesale Tile, LLC

SERIES NAME

ORIGIN

### TECHNICAL CHARACTERISTICS

Available Formats:	12x24		
Style Description:	Marble	Glaze Application Method:	Inkjet
Visual Characteristics:	Polished Marble	Number of Faces/Screens:	10, Light Grey: 14
Thickness in mm:	9.0 MM	Number of Punches/Molds:	
Modular Suitability:		Body Type:	Porcelain
Application:	Residential/Commercial	Color Body Unglazed:	
Recycled Content: Post or Pre Customer		Surface Type:	Glossy/Polished/Flat
Rectified or Pressed	Rectified	Recommended Grout Joint:	

### PRODUCT TESTING INFORMATION

*Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)*

Water Absorption:	<0.05-0.12%	Static COF:	
Shade Variation (1, 2, 3, 4)	V2	Dynamic COF:	.22 Polished
Scratch Hardness (MOHS)	4.5	Breaking Strength:	2,100-2237 N
Frost Resistant:	Yes	Thermal Shock Resistance:	Pass after 10 cycles
PEI/Abrasion Resistance:	2	Deep Abrasion Test <175mm <sup>2</sup> :	No
Chemical Resistance:	GA/GLA/GHA		

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.