NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

SERIES NAME

EVOLUTION

| TECHNICAL CHARACTERISTICS | | | | |
|---------------------------|------------------------|---------------------------|-----------------------|--|
| Available Formats: | 12x24, 24x24, 24x48 | | | |
| Style Description: | Stone | Glaze Application Method: | Inkjet | |
| Visual Characteristics: | Stone | Number of Faces/Screens: | 24x48: 12, 24x24: 24, | |
| | | | 12x24: 48 | |
| Thickness in mm: | 9 MM | Number of Punches/Molds: | 4 | |
| Modular Suitability: | Yes | Body Type: | Porcelain | |
| Application: | Residential/Commercial | Color Body Unglazed: | Yes | |
| Recycled Content: | Pre customer 30% | Surface Type: | Matte/Textured | |
| Post or Pre Customer | | | | |
| Rectified or Pressed | Rectified | Recommended Grout Joint: | 2 mm | |

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

| | 0.05% | CL 11 COF | |
|------------------------------|-----------|---------------------------|------------|
| Water Absorption: | <0.05% | Static COF: | |
| Shade Variation (1, 2, 3, 4) | V3 | Dynamic COF: | >0.42 |
| Scratch Hardness (MOHS) | 7 | Breaking Strength: | ≥40N/sq mm |
| Frost Resistant: | Yes | Thermal Shock Resistance: | Resistant |
| PEI/Abrasion Resistance: | 5 | Deep Abrasion Test | Yes |
| | | <175mm ² : | |
| Chemical Resistance: | Resistant | | |

Note:

Manufacturer does not recommend installing large format rectangular tile using a 50% staggered brick/running bond grout joint pattern. Joint locations can be random and should be positioned to be no less than 30% the length of the adjacent tile. Alternating joints so they are <30%, a straight-lay or herring bone patterns are acceptable and with grout joint sizes of 1/4" to 3/16" but no less than 1/8".