

NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

SERIES NAME

HYDRA ISLES

TECHNICAL CHARACTERISTICS

Available Formats:	20x20		
Style Description:	Stone	Glaze Application Method:	Inkjet
Visual Characteristics:	Stone	Number of Faces/Screens:	6
Thickness in mm:	9 mm	Number of Punches/Molds:	1
Modular Suitability:	Yes	Body Type:	Porcelain
Application:	Residential/Light Commercial	Color Body Unglazed:	
Recycled Content: Post or Pre Customer		Surface Type:	MATTE
Rectified or Pressed	Rectified	Recommended Grout Joint:	2 MM

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

Water Absorption:	0.5%	Static COF:	
Shade Variation (1, 2, 3, 4)	2	Dynamic COF:	Dry: .70 Wet: .37
Scratch Hardness (MOHS)		Breaking Strength:	
Frost Resistant:	Yes	Thermal Shock Resistance:	Yes
PEI/Abrasion Resistance:	4	Deep Abrasion Test <175mm ² :	
Chemical Resistance:	Yes		

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.

NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

SERIES NAME

HYDRA ISLES

TECHNICAL CHARACTERISTICS

Available Formats:	12x24 & 3x3 Mosaic		
Style Description:	Stone	Glaze Application Method:	Inkjet
Visual Characteristics:	Stone	Number of Faces/Screens:	12
Thickness in mm:	9 mm	Number of Punches/Molds:	1
Modular Suitability:	Yes	Body Type:	Porcelain
Application:	Residential/Light Commercial	Color Body Unglazed:	
Recycled Content: Post or Pre Customer		Surface Type:	MATTE
Rectified or Pressed	Rectified	Recommended Grout Joint:	2 MM

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

Water Absorption:	0.5%	Static COF:	
Shade Variation (1, 2, 3, 4)	2	Dynamic COF:	Dry: .70 Wet: .37
Scratch Hardness (MOHS)		Breaking Strength:	
Frost Resistant:	Yes	Thermal Shock Resistance:	Yes
PEI/Abrasion Resistance:	4	Deep Abrasion Test <175mm ² :	
Chemical Resistance:	Yes		

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacturer. Use constitutes acceptance.