

NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

SERIES NAME

VENATTO

TECHNICAL CHARACTERISTICS

Available Formats:	10x60		
Style Description:	Wood look	Glaze Application Method:	Inkjet
Thickness in mm:	9.5 mm	Number of Faces/Screens:	24
Modular Suitability:	Yes	Number of Punches/Molds:	3
Application:	Residential, Commercial, Wall	Body Type:	Porcelain
Rectified or Pressed:	Rectified	Color Body:	Unglazed
Recycled Content: Post or Pre Customer		Surface Type:	Matte
		Recommended Grout Joint:	2 mm

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

Water Absorption:	<0.15%	Chemical Resistance:	OAK LA-HA ALMOND/CHESTNUT LA-HA-HB
Shade Variation (1, 2, 3, 4)	3	Dynamic COF:	>.42
Scratch Hardness (MOHS)		Breaking Strength:	2293 N
Frost Resistant:	Yes	Thermal Shock Resistance:	Resistant
PEI/Abrasion Resistance:	V	Deep Abrasion Test <175mm ² :	Yes

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacture. Use constitutes acceptance.

NEW PRODUCT SERIES

Technical Information Spec-sheet



International Wholesale Tile, LLC

SERIES NAME

VENATTO WALL

TECHNICAL CHARACTERISTICS

Available Formats:	24x48		
Style Description:	Wood look	Glaze Application Method:	Inkjet
Thickness in mm:	10.5 mm	Number of Faces/Screens:	7
Modular Suitability:	Yes	Number of Punches/Molds:	2
Application:	Wall Only	Body Type:	Porcelain
Rectified or Pressed:	Rectified	Color Body:	Unglazed
Recycled Content: Post or Pre Customer		Surface Type:	Matte
		Recommended Grout Joint:	2 mm

PRODUCT TESTING INFORMATION

Please Note: All tests are completed per the US standards determined by the Tile Council of North America (TCNA)

Water Absorption:	<0.15%	Chemical Resistance:	LA-HA
Shade Variation (1, 2, 3, 4)	3	Dynamic COF:	
Scratch Hardness (MOHS)		Breaking Strength:	2376 N
Frost Resistant:	Yes	Thermal Shock Resistance:	Resistant
PEI/Abrasion Resistance:		Deep Abrasion Test <175mm ² :	Yes

ANSI A108.02 Section 4.3.8.2 states that for running bond/joint brick patterns utilizing tiles (square or rectangle) where the side being offset is greater than 14" (nominal dimension), the running bond offset will be a maximum of 33% unless otherwise specified by the manufacture. Use constitutes acceptance.